# Technical Data Sheet





## THE CLEAR MATERIAL

VITRA 413 is a photosensitive material for DWS stereolithography 3D printers, developed for high definition functional prototypes and for general applications. It is a clear, standard acrylic material.

#### HINTS FOR THE DESIGN

VITRA 413 is suitable both for thin and thick models. It is the ideal material to obtain smooth and precise clear samples.

## **THE VITRA SERIES**

The Vitra series includes all the materials suitable for the production of transparent prototypes and clear functional parts. These materials are extremely accurate and precise and were developed in-house by DWS.

## **FEATURES**

- Smooth Surfaces
- Transparent
- High Resolution and Precision
- High Accuracy

#### TECHNICAL FEATURES OF THE LIQUID MATERIAL

Environmental Values for Use	22°C - 27°C - max, RH 40% - 60%
Appearance / Colour	Liquid / Light Yellow
Viscosity	600 ~ 900 mPa•s at 25°C
Density	1,05 g/cm <sup>3</sup>

#### TECHNICAL CHARACTERISTICS OF THE RESIN AFTER UV CURING

Elongation at Break (%)	2~3
Surface Hardness (Shore D)	86 ~ 88
Tensile Strength (MPa)	20 ~ 40
Tensile Modulus (MPa)	1500 ~ 2250
Flexural Strength (MPa)	60 ~ 115
Flexural Modulus (MPa)	1750 ~ 2650
HDT@0,46MPa	54 ~ 58
Application / Use	Transparent Prototypes, Clear Functional Parts

Technical specification subject to change without notice.



